

## TOUCH WOOD PU PRIMER (INT)

### Product Description

Touchwood Polyurethane Pigmented Primer is based on suitably modified polyester containing zinc stearate, titanium dioxide and other additives in combination with suitable catalyst provides a tough, durable and hardwearing low sheen finish with good flow and film build-up. In addition this product has:

- Excellent leveling and very fast sanding time leading to high throughput
- Good hiding of the base
- Smooth surface for subsequent topcoats
- Good resistance to household chemicals and beverages

### Recommended Areas Of Application

**Area of Use:** Interior only

**Substrate:** Wood and related substrates

### Technical Data

**Sheen Variants:** Low sheen, Smooth

**Colours:** White

**% Solids (NVM):** 56 ± 2

Theoretical Covering Capacity		
Recommended Dry Film Thickness per Coat		Theoretical Spread Rate m <sup>2</sup> / ltr
<b>Minimum</b>	30 microns	13.30 m <sup>2</sup> / ltr.
<b>Maximum</b>	50 microns	8.00 m <sup>2</sup> / ltr.
<b>Typical</b>	40 microns	10.00 m <sup>2</sup> / ltr.

Practical Covering Capacity	
For estimation of practical covering capacity, following factors to be taken into account: surface profile, uneven application, over spray, losses in container and equipment etc.	

Drying Time	Substrate Temp.	Sandable Dry	Overcoating Interval	
			Minimum	Maximum
	25°C	2 hours	4 hours	Indefinite
	35°C	60 minutes	2 hours	
	45°C	45 minutes	1.5 hours	
This is a two pack product. Mixing ratio of base to catalyst is 2:1 by volume.				

Application Data	<b>Method of Application</b>	Conventional spray application.
	<b>Part B</b>	Touchwood PU Hardener # 1
	<b>Thinner</b>	Berger Touchwood PU Thinner
	<b>Thinning Ratio (by vol.)</b>	Use 10% to 15% for ease of application depending on the gun type.
	<b>Available Pack Size</b>	5 USG and 1 USG

### Surface Preparation

- Sand the wood surface (new or previously painted) thoroughly using P 180 emery paper first, followed by P 400 emery paper.
- Dust off the surface using rags and wipe off with P.U. Thinner to remove traces of oil, grease, or any organic contaminants. In case of hard wood, make sure it is seasoned for appropriate time prior to application of coating system to ensure minimum quantity of moisture is present.
- Presence of moisture in the wood may cause blistering and poor curing of Acrylic PU system which may ultimately flake off in a short time after application.

### Application Details

- Ensure adequate ventilation during application and drying.
- Do not apply when humidity exceeds 85% and condensation is likely.
- Surface temperature should be 3°C or more above dew point.
- Stir the contents thoroughly before and during use, with a broad flat stirrer, using an upward lifting action.
- Mix Base and Hardener thoroughly and full quantity.
- Conventional Spray: Tip Size : 1.4mm  
Pressure : 40 – 50 bar.
- Brush or Roller: Recommended only when the area is not.

### TYPICAL PAINT SYSTEM

<b>Timber</b>
1 or 2coats x Touchwood PU primer white
1 or 2coats x Touchwood PU pigmented Topcoats
For detailed system recommendation based on specific requirements please contact Berger representative.

### Storage, Safety Information And Precautions

- Keep out of reach of children.
- Store in cool, dry conditions; ensure adequate ventilation during application.
- Avoid contact with skin and eyes; wear suitable protective clothing such as overalls, goggles, dust masks and gloves.
- Flash Point : 23° C
- Shelf life up to 12 months from the date of manufacture.

### First Aid

- Eyes: In the event of accidental splashes, flush eyes with water immediately and obtain medical advice.
- Skin: Wash skin thoroughly with soap and water or approved industrial cleaner.
- Inhalation: Move patient to fresh air, loosen collar and keep patient rested.
- Ingestion: Do not induce vomiting. Obtain immediate medical attention.
- Dispose in landfill only.

### Disclaimer

The information provided in this data sheet is not intended to be complete. It is the responsibility of the user to ensure that the product used is suitable for the purpose it is meant to serve. In view of various factors affecting the performance of the coating, we cannot assume responsibility for the product performance, nor do we accept any liability arising from use of this product, unless specifically agreed to in writing by us. The information provided in the datasheet may be modified by us without notice.

*“This Technical Data Sheet supersedes those previously issued with immediate effect  
For more information please contact us at: [customerservice.oman@asianpaints.com](mailto:customerservice.oman@asianpaints.com)”*

**Asian Paints (Middle East) LLC**  
Ghala Industrial Area, Al - Khuwair  
Postal Code : 133, P.O Box :462  
Sultanate of Oman